# The Samphire Project: A distal IOCG and evidence for Mesoarchean crust in the Gawler Craton

Thesis submitted in accordance with the requirements of the University of Adelaide for an Honours Degree in Geology

Samuel David Goldsmith November 2014



## THE SAMPHIRE PROJECT: A DISTAL IOCG AND EVIDENCE FOR MESOARCHEAN CRUST IN THE GAWLER CRATON

### THE SAMPHIRE PROJECT: A DISTAL IOCG

#### ABSTRACT

The Samphire project on the north eastern Eyre Peninsula contains proven uranium resources. These are in paleochannel-like deposits hosted within saprolite that has a granite origin. This granite forms the bedrock of the area and is of a batholith scale termed the Samphire batholith. Alteration takes the form of hematite, quartz and fluorite, forming vein assemblages that display cross cutting relationships. Characterization of this alteration by scanning electron microscope and geochemical analysis suggests this alteration strongly resembles iron oxide-copper-gold alteration that is seen through out the Gawler Craton. U-Pb dating of zircon, thorite and hematite is used to provide reconnaissance geochronology for age of the host granite and also stages of alteration. The summation of results from these techniques, creates a genetic model with the suggestion of the origin of the uranium in the overlying cover from the bedrock granite.

### SAMPHIRE, GAWLER CRATON, BEDROCK, MESOARCHEAN, IOCG, U-PB GEOCHRONOLOGY

### **TABLE OF CONTENTS**

The Samphire Project: A distal IOCG and evidence for Mesoarchean crust in the	
Gawler Craton	1
Abstract	i
Samphire, Gawler Craton, BEDROCK, Mesoarchean, IOCG, U-Pb Geochronology	i
List of Figures	3
List of Tables	5
Introduction	6
Geological Background	8
Geodynamic Setting	8
IOCG Mineralization within the Galwer Craton	. 10
The Samphire Project	.11
Methods	.12
Approach and Sampling	.12
Analytical	. 13

Observations and Results	14
Petrography	14
Samphire Granite	14
Rock forming minerals	17
Fe-(Ti)-oxides (hematite, magnetite and ilmenite)	19
Sulphides	21
Accessory minerals	22
LA-ICP-MS trace element data	29
Iron-oxides	29
Magnetite and ilmenite	
Fluorite	
U-Pb geochronology	
Zircon U-Pb	
Sample 751003	40
Sample 751002	40
Sample 845007	41
Thorite U-Pb	
Sample 751003	43
Sample 751002	45
Hematite U-Pb	45
Discussion	46
Petrography and mineral geochemical signatures	47
Geochronological constraints	51
Towards a genetic model	53
Practical implications	55
Conclusions	56
Acknowledgments	56
References	57
Appendix A: LA-ICP-MS Methodology	59
LA-ICP-MS trace element spot analysis	59
LA-ICP-MS element mapping	60
U-Pb dating methodology	61
References	
Appendix B1: U-PB dating of zircon	64
Appendix B2: U-Pb dating of thorite	65
Appendix B3: U-pb dating of hematite	70

### LIST OF FIGURES

Figure 1 a) Location map EL4979 within South Australia and relative lithologies. Inset map provides extend of crystalline basement of the Gawler Craton. b) Bouguer anomaly removed gravity map of prospect area with drillhole data. Data compiled in ESRI's ARCgis using data sets from SARIG with drillhole location and gravity map provided by Uranium SA......8 Figure 2 Schematic diagram showing drillcore lithologies and alteration with depth (m) and sample locations. Above 105 m is undifferentiated saprolite and cover sequence. 12 Figure 3 Photos of drill core samples showing textural and compositional variations within Samphire granite. a) 37 cm section from MRM751 with porphyritic texture. b) Fluorite 'flooding' texture towards right hand side with distinct purple colour compared to the left hand section. c) Quartz rich vein containing wall rock clasts with chlorite alteration. Gap between sections is a cavity that is 5 cm in size. Below cavity is a 8-10 cm section of porphyritic texture. d) A hydrothermal 'boiling' texture with very dominant hematite alteration and prominent vugs intersected for 20 cm. e) 4 cm thick fluorite vein with earth hematite overprint. f) hematite vein-let swam imparting breccia-Figure 4 BSE images (a-i) showing hematite textures. Reflected light images (j-l) allow distinction hematite from magnetite. a) Fine-grained aggregates of acicular hematite in quartz groundmass displaying no preferred orientation with quartz grains and clay infilling fracture space. b) Coarse, acicular hematite in a vein with fine hematite in between. c) Small quartz-bearing vein with coarse acicular hematite displaying fractures. Finer-grained hematite is also growing within the vein and in veinlets in Kfeldspar. d) Fine-grained aggregates of hematite with a fibrous texture in K-feldspar showing a similar fibrous texture surrounded by homogenous quartz. e) Skeletal hematite with quartz in a clay-rich sample displaying voids. f) Hematite as rims on Kfeldspar-albite intergrowths. g) Isolated hematite grain with a very slightly vuggy texture in a quartz vein crosscutting K-feldspar with fluorite on rim. h) Porous, blebby, clustered hematite with K-feldspar-quartz inclusions. The bright patch is pyrochlore. i) Hematite grains clustered with zircons and thorite in fluorite and albite. Calcite fills the space between these grains and as veins in the lower fluorite. j) Porous, blebby hematite showing magnetite cores with fine-grained, interstitial hematite. Metamict zircon is present at the bottom of the image. k) Coarse acicular, homogeneous hematite. l) Rutile-Figure 5 a) Euhedral pyrite within a vug on fluorite-quartz vein margin. Heavily metamict and fracture zircon is present; co--existing K-feldspar has a dusty appearance. Small aggregates of fine, REE-Th-(U)-enriched minerals can be seen growing in the vug. b) Quartz-fluorite vein with coarse and fine pyrite growing close to phase boundaries. K-feldspar has dusty appearance and fluorite veins. c) Pyrite forming rims on thorite grains in a quartz-fluorite vein containing fine-grained hematite. d) Coarse, fractured pyrite containing inclusions of fluorite. e) Fine-grained pyrite clusters in a void within K-feldspar-albite. K-feldspar has dusty appearance at the bottom of the image but the grains within the void are lath-shaped and not dusty. f) Coarse-grained pyrites in a quartz vein. Top pyrite grain is anhedral and has is surrounded by void

space into which fine, acicular REE-Th-U-minerals are growing. K-feldspar displays a Figure 6 a) Anhedral sphalerite within vuggy calcite with an inclusion of euhedral fluorite, hosted in a quartz-K-feldspar groundmass. This sample displays a high proportion of calcite compared with many other samples, and also features abundant synchysite. b) Coarse-grained molybdenite with rims of pyrite-chalcopyrite symplectites (shown in detail in [d]). c) Galena rims forming on elongate chalcopyrite with cores of pyrite. Voids are found close to the pyrite cores and one pyrite is within a void. This assemblage contains significant void space hosting fibrous REE-minerals. The assemblage is hosted in a fluorite-bearing vein. d) Anhedral pyrites with chalcopyrite infill forming a symplectite close to molybdenite. Halite grains can be seen above feldspar (K-feldspar?) that displays a 'wormy' texture. e) Coarse euhdral pyrite with fine anhedral pyrite present between grains with some clay alteration. Coffinite veins form rims and inside voids in the coarse pyrite. Coffinite also surrounds fine-grained pyrite. Quartz fills void space in this assemblage. f) Fine-grained pyrite with uraniumbearing inclusions (coffinite?) in a clay-bearing vein that contains thin laths of biotite with rutile inclusions. A small monazite displaying some internal zonation represents an Figure 7 a) Coarse, anhedral synchysite displaying thin lamella of bastnäsite. An inclusion within this grain contains a silica-bearing Fe-oxide signature – probably an intergrowth of quartz and hematite/magnetite. The grain is located on the contact of porous quartz with acicular, vein hematite and dusty K-feldspar. b) Fragmented synchysite grains containing lamella/aggregates of bastnäsite within rich zone of clay alteration. Bastnäsite displays a thin acicular crystal habit and does occur outside of synchysite grains. c) Synchysite vein in quartz. d) Calcite veins in fluorite containing synchysite. e) Coarse and porous synchysite with fine-grained thorite-monazite in a calcite-fluorite groundmass. From previous images there is a possibility of some bastnäsite within the synchysite although the acicular habit is not prominent. g) Heavily altered apatite with synchysite inclusions and minor monazite. Area is heavily altered with void space, REE fibres, metamict zircon and clay alteration. h) Thorite-apatite assemblage with clear zonation within the apatite. Thorite also displays some zonation the reason for this zonation in apatite and thorite was not discernible via EDS analysis. Porous ilmenite can be seen in the top of the frame sharing a transitional boundary with fine grained hematite. i) Heavily altered apatite with thorite. A K-feldspar grain displays small voids imparting a porous texture. Several rutile grains in a clay groundmass. j) Heavily altered ilmenite containing both rutile and fine-grained hematite. Quartz has fractured this mineral but morphology is maintained. k) Coarse zircon in dusty albite, displaying strongly metamict texture including internal zonation and fracturing. 1) Fractured zircon with some zonation with a rim of fine-grained hematite located in a Figure 8 a) Back scatter electron images showing aspects of REE- and U- mineralogy. (a) Coarse pyrite (Pyr) with significant fracturing and pore space filled with coffinite (Cof). Coffinite veins also fill fractures in quartz (Qtz). b) Fine coffinite and coexisting rutile (Rtl) at grain boundary between quartz and K-feldspar. Coffinite is also present within cleavage planes in biotite. c) Strongly-altered rutile displaying coffinite replacement/infill in a very porous albite (Alb) groundmass. Pyrite displays some alteration but is not strongly affected by coffinite. d) Intense alteration of a biotite lath with rutile developed along grain boundaries. Coffinite forms a thick rim about this

mineral and breaches into the grain along fracture/cleavage. e) Coffinite veins in an albite groundmass. Synchysite (Syn) also occurs within this vein but does not contain Figure 9 REY Fractionation trends for hematite and fluorite (a-d) and BSE images (e-f) Figure 10 Geochemical discriminant diagrams for different types of hematite. See text Figure 11 LA-ICP-MS element maps of bladed hematite (sample 751008). Note internal compositional zonation (sets of zones perpendicular to the long axis of each lamellae) with respect to Ti, Sn, W, Nb, Ta and V. Note that part of the aggregate is depleted in Ce, Y, U and Th. Note also partial replacement of Ba-bearing K-Feldspar (at the top) by albite. Scale bars are counts per second. Log scale bars are used for elements; Al, Nb, Sn, Ta, Ti, U V, W and Y. The log scale bars are  $10^n$  where *n* is the number on the scale Figure 12 Zircon Concordia. (a) 751003 zircon concordia all spots; (b) 751002 zircon concordia all spots; (c) 845007 zircon concordia grain 1; (d) 751003 zircon concordia separated by grain; (e) 751002 zircon concordia separated by grain; (f) 845007 zircon Figure 13 Thorite Concordia. (a) 751003 thorite Concordia all spots; (b) 751002 thorite Concordia all spots; (c) 751003 thorite Concordia grain 1; (d) 751003 thorite Concordia grain 2; (e) 751002 thorite Concordia population 1; (f) 751002 thorite Concordia Figure 14 Hematite Concordia. a) 751003 and 751008 all data. Note some spots lie off displayed plot area; b) 751003 and 751008 data filtered as per relevant text. All ellipses Figure 15 Schematic diagram summarasing results of this study in the context of the Figure 16 Schematic cross-section showing location of uranium of uranium mineralization in the Samphire project area relative to bedrock (Uranium SA 2013)...54

### LIST OF TABLES

Table 1 Index of sample suite	
Table 2 LA-ICP-MS data for hematite and other Fe-(Ti)-oxides	
Table 3 LA-ICP-MS data for rock fluorite	
Table 4 LA-ICP-MS data for vein fluorite.	